

Technical data sheet without Mid sole

Ref : 45816 S1 BRISTOL

CE Attestation N°:

Extension code :

Revision date : 20/04/2009

<u>THE SOLE</u>			<u>THE UPPER</u>		
	MTS	Norm		MTS	Norm
Resistance to shock			<i>Colour</i> GRIS	<i>Thickness</i> 2 / 2.2	1.5
Clear space in mm at impact	14.00	>14	Material used	Microsuede 2 mm col gris L 140	
Resistance to crushing			Resistance to tearing	Yes	>120
Clear space in mm under 15000N of constraint	19.50	>14	Permeability to water vapor (mg/cm2.h)	3.90	>0.8
Conformity of the staples	Yes	Yes	Water vapor facor (mg/cm2)	45.00	>15
Sole width in mm	6.00	>4	Leather acidity (pH)		
Staple height in mm	3.00	>2.5	Time or the water to pass through in minutes		
Resistance of tearing in kN/m	11.00	>8	Quantity of water absobed in % after 1h		
Resistance to abrasion : density	1.15	>0.9	Difference index	0.00	<0.7
Resistance to abrasion : loss of volume (mm3)	20.00	<150	<u>THE LINING OF THE FRONT PART</u>		
Hydrolysis (increase of the notch in mm after 150.000 flexions)	0.00	<6	Material used	Non tissé aiguilleté blanc	
Resistance to hydrocarbons (Increase in volume in %)	3.00	<12	Thickness	1.1	0.8
Necessary force to perfore the sole (N)			Abrasion : testing in dry atmosphere	>25600	25600
Conformity of the sole	Yes	Yes	Abrasion : testing in humid atmosphere	>12800	12800
Conformity of the mid-sole dimensions	Yes	Yes	Permeability to water vapor (mg/cm2.h)	24	>2
Antistatism : resistance to dry atm. (megaohms)	448	0.1<V<1000	Water vapor factor (mg/cm2)	189	>20
Antistatism : resistance to humid atm. (megaohms)	20	0.1<V<1000	<u>THE INSOLE</u>		
Heel shock absorber	29	>20		2.2	2
Resistance of the upper/sole adherence (N/mm)	5.30	>4	Matériau Cellulosique (mm)		
			Water absorption in %	81	>35
			Water desorption in %	99	>40
			Cycles needed to obtain the tearing of the surface	>400	400
Slip resistance EN ISO 20345:A1 SRA Ceramic	0.39	>=0.32	<u>THE SEWING THREAD</u> 100 % Polyamide		
Slip resistance EN ISO 20345:A1 SRB Steel	0.21	>=0.18	<u>THE LACES</u> 100 % Polyester - Embout en Acetate de Cellulose		

Sole specification :

ANNIC S.A.S. 82250 LAGUEPIE Tél. : +33 (5) 63 30 21 01 - Fax : +33 (5) 63 31 40 18

Web : <http://www.mts-morethansafety.com> E-mail : contact@morethansafety.com

S.A.S. au capital de 573.840 € - R.C. B778 115 436 - Siret 778 115 436 00017 - APE : 193 Z - TVA CEE : FR 95 778 115 436

Model specification :