



Its high whiteness and perfectly smooth surface of DCP Green promote a high quality reproduction. Its high opacity guarantees double-sided printing.

Substance	gsm	NF EN ISO 536	(+/-2,5%)	90	100	120	160	200	250
Thickness	µm	NF EN ISO 534	(+/-5)	95	105	126	168	199	250
Bulk	cm ³ /g	NF EN ISO 534		1.05	1.05	1.05	1.05	1.00	1.00
Whiteness	CIE	NF ISO 11475	(+/-3,5%)	135	135	135	135	135	135
	ISO	ISO 2470-2		97	97	97	97	97	97
Opacity	%	NF ISO 2471	(+/-3)	95	97	98	>99	>99	>99
Bekk smoothness	s	NF ISO 5627	{??}	110	110	110	110	110	110

Application

External communication. All documents containing text and colors. Reproduction of images.

Product certificates and technical information

- Resistant to ageing (ISO 9706)
- ColorLok technology



Product certificates and environmental information

- Angle Bleu
- FSC®
- Ecolabel



www.blauer-engel.de/uz14a



The mark of responsible forestry



Information for printing

- Certified for professional dry toner systems (DIN / EN 12281)
- Recommended for copiers, laser printers and inkjet systems
- Plain paper setting for inkjet printing

Mill certifications

- ISO 14001: Environmental management system
- ISO 9001: Quality management system
- ISO 50001: Energy management system

Made in France

Indicative values. Errors and omissions excepted. Subject to change without notice.
Revision date: 29/03/2021