

AVERAGE CHARACTERISTICS			
GRADE	Lyreco colours		
Fibre composition	ECF		
Medium	neutral		
Substance	160	g/m²	NF EN ISO 536 NFQ 03 019
Thickness	210	microns	NF EN ISO 534 NFQ 03 016
Bulk	1,31	cm³/g	NF EN ISO 534 NFQ 03 016
Bendtsen smoothness	180	ml/min	ISO 8791-2 NF Q 03-049
Absolute humidity	5,50	%H₂O	NF EN ISO 20287 NFQ 03 003
Relative humidity	42	in the air	sword
Permanence	ISO 9706		NF EN ISO 9706