

#### **TECHNICAL DATA SHEET**

#### **Office Premium Cut-Size**

## **Physical Parameters**

	REFERENCE	TARGET	TYPICAL	. VALUES
Basis Weight, g/m <sup>2</sup>	ISO 536	100	96.0	104
Thickness, µm	ISO 534	120	116	124
Stiffness MD, mN	ISO 2493-1		≥ 170	
Stiffness CD, mN	ISO 2493-1		≥ 60	
Tensile MD, kN/m	ISO 1924-2		≥ 7.0	
Bendtsen Roughness, ml/min	ISO 8791-2	100	60	140
Air Permeability, ml/min	ISO 5636-3			≤ 1700
Moisture, %	ISO 287	4.0	3.5	4.5
Formation, #	Internal Method		≥ 40	

# **Optical Parameters**

	REFERENCE	TARGET	TYPICAL	VALUES
Whiteness, CIE	ISO 11475	169	166	172
Brightness D65, %	ISO 2470-2	112	109	115
Opacity, %	ISO 2471	97	≥ 95	

The product specifications provided hereby can be changed on one or more parameters at any time by The Navigator Company

Approved by:

Technical Department: Eng. Vitor Crespo

sgftp / ftp\_sheets 1 / 1 FTP-PAP-0005 Rev.: 007 - Data: 2017/11/14 Page: Printed on: 2021/03/10 10:03:42

ccmtest



### **QUALITY AND ENVIRONMENTAL INFORMATION**

- The Navigator Company's papers are made from Elemental Chlorine Free (ECF) bleached kraft pulp;
- The Navigator Company's papers are produced in a neutral/slightly alkaline papermaking process, therefore considered as "acid free" products which meet the requirements of ISO 9706 standard, "Information and documentation – Paper for documents – Requirements for permanence";
- The Navigator Company's laboratories are accredited according to the ISO 17025 standard;
- Quality, Environmental and Safety Management Systems are certified according to the ISO 9001, ISO 14001 and OHSAS 18001 standards.
- The Navigator Company is chain-of-custody certified according to standards FSC-STD-40-004 and FSC-STD-40-005 (NC-COC-014433/NC-CW-014433) and to standard PEFC ST 2002:2013 (APCER/2007/CDR.0008).