



REY TEXT+GRAPHICS 120G

| Parameters | Standard Used | Units | Measured |
|------------|---------------|------------------|------------------------------------|
| Substance | ISO 536 | g/m ² | 120 +/- 2 |
| Thickness | ISO 534 | µm | 133 +/- 3 |
| Bulk | ISO 534 | | 1,11 |
| Moisture | ISO 287 | % | |
| Smoothness | ISO 5627 | Bekk sec | 65 +/- 15 |
| Formation | Kajaani | Kajaani Index | |
| Whiteness | ISO 11475 | CIE | 170 +/- 2 |
| Opacity | ISO 2471 | % | 97 +/- 2 |
| Stiffness | ISO 2493 | m/N | 260 +/- 15 (MD) 150 +/- 15 (CD) |
| Porosity | | | |

References:

- * ISO 14001 - Environmental
 - * ISO 18001 - OHSAS - Health & Safety
 - * ISO 9001:2000 - Quality Systems
 - * ISO 9706 - Ageing Resistance
-