



REY TEXT+GRAPHICS 80G

Parameters	Standard Used	Units	Measured
Substance	ISO 536	g/m ²	80 +/- 2
Thickness	ISO 534	µm	100 +/- 3
Bulk	ISO 534		1,25
Moisture	ISO 287	%	
Smoothness	ISO 5627	Bekk sec	55 +/- 15
Formation	Kajaani	Kajaani Index	
Whiteness	ISO 11475	CIE	170 +/-2
Opacity	ISO 2471	%	92 +/- 2
Stiffness	ISO 2493	m/N	120 +/- 15 (MD) 40 +/- 15 (CD)
Porosity			

References:

- * ISO 14001 - Environmental
 - * ISO 18001 - OHSAS - Health & Safety
 - * ISO 9001:2000 - Quality Systems
 - * ISO 9706 - Ageing Resistance
-