

| Average characteristics | | | |
|--------------------------------|------------|----------------------------------|-------------------------------|
| Grade : | 2800 Laser | | |
| | | unit | |
| Forestry certification | FSC | | |
| Fibre composition | ECF | | |
| Medium | neutral | | |
| Substance | 80 | g/m ² | NF EN ISO 536 NFQ 03 019 |
| Thickness | 108 | microns | NE EN ISO 534 NFQ 03 016 |
| Bulk | 1,35 | cm ³ /g | NE EN ISO 534 NFQ 03 016 |
| Whiteness | 170 | CIE | NF ISO 11475 NFQ 03 099 |
| | 116 | ISO | ISO 2470 NFQ 03 039 |
| Bendtsen smoothness | 160 | seconds | NF ISO 5627 NFQ 03 012 |
| Absolute humidity | 4,50 | %H ₂ O | NF EN ISO 20287 NFQ 03 003 |
| Relative humidity | 30 | % H ₂ O in the air | sword |
| Opacity on paper background | 94 | % | NF ISO 2471 NFQ 03 040 |
| Kajaani formation | 91 | | |
| Permanence | ISO 9706 | | NF EN ISO 9706 |

The values given are average measurements and are not a specification as such