

## Bacterial Filtration Efficiency (BFE) and Differential Pressure (Delta P) Final Report

Test Article: Face mask Model.3030  
Purchase Order: 19SGB-0206  
Study Number: 1149902-S01  
Study Received Date: 08 Feb 2019  
Testing Facility: Nelson Laboratories, LLC  
6280 S. Redwood Rd.  
Salt Lake City, UT 84123 U.S.A.  
Test Procedure(s): Standard Test Protocol (STP) Number: STP0004 Rev 15  
Deviation(s): None

**Summary:** The BFE test is performed to determine the filtration efficiency of test articles by comparing the bacterial control counts upstream of the test article to the bacterial counts downstream. A suspension of *Staphylococcus aureus* was aerosolized using a nebulizer and delivered to the test article at a constant flow rate and fixed air pressure. The challenge delivery was maintained at  $2.8 \times 10^3$  colony forming units (CFU) with a mean particle size (MPS) of  $3.0 \pm 0.3 \mu\text{m}$ . The aerosols were drawn through a six-stage, viable particle, Andersen sampler for collection. This test method complies with ASTM F2101-14 and EN 14683:2014, Annex B, and AS4381:2015, with the exception of the higher challenge level, which may represent a more severe test.

The Delta P test is performed to determine the breathability of test articles by measuring the differential air pressure on either side of the test article using a manometer, at a constant flow rate. The Delta P test was designed to comply with MIL-M-36954C, Section 4.4.1.2 and complies with EN 14683:2014, Annex C and AS4381:2015.

All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

Test Side: Inside  
BFE Test Area:  $\sim 40 \text{ cm}^2$   
BFE Flow Rate: 28.3 Liters per minute (L/min)  
Delta P Flow Rate: 8 L/min  
Conditioning Parameters:  $85 \pm 5\%$  relative humidity (RH) and  $21 \pm 5^\circ\text{C}$  for a minimum of 4 hours  
Test Article Dimensions:  $\sim 174 \text{ mm} \times \sim 160 \text{ mm}$   
Positive Control Average:  $2.8 \times 10^3$  CFU  
Negative Monitor Count:  $< 1$  CFU  
MPS:  $3.2 \mu\text{m}$



  
Curtiz Louwer  
Study Director

For  
Janelle R. Bentz, M.S.

22 Feb 2019  
Study Completion Date



1149902-S01

**Results:**

Test Article Number	Percent BFE (%)	Delta P (mm H <sub>2</sub> O/cm <sup>2</sup> )	Delta P (Pa/cm <sup>2</sup> )
1	99.9	3.5	34.4
2	99.6	3.1	30.8
3	99.9	3.4	33.2

The filtration efficiency percentages were calculated using the following equation:

$$\% BFE = \frac{C - T}{C} \times 100$$

C = Positive control average

T = Plate count total recovered downstream of the test article

Note: The plate count total is available upon request