

TECHNICAL DATA SHEET			
GRADE	1857/1858 DCP		
		unit	
Pulp	100%ECF		
Medium	neutral		
Substance	250	g/m2	NFQ 03 019
Thickness	250	microns	NFQ 03 016
Bulk	1	cm3/g	NFQ 03 016
Whiteness	168 116	CIE ISO	NFQ 03 099 NFQ 03 039
Bekk smoothness	90	seconds	NFQ 03 012
Absolute humidity	4,5	%H2O	NFQ 03 003
Relative humidity	30	% H2O in the air	sabre
Opacity on paper background	99	%	NFQ 03 040

This paper is a permanent paper as per the ISO 9706 norm

This paper is made from 100% chemical woodfree pulp

The values given above are averages and do not constitute a spec.