

<b>Average characteristics</b>				
<b>GRADE</b>	<b>Trophée tints</b>			
<b>Forestry certification</b>	<b>FSC</b>			
<b>Fibre composition</b>	<b>ECF</b>	<b>ECF</b>		
<b>Medium</b>	<b>neutral</b>	<b>neutral</b>		
<b>Substance</b>	<b>80</b>	<b>160</b>	<b>g/m2</b>	NF EN ISO 536 NFQ 03 019
<b>Thickness</b>	<b>109</b>	<b>210</b>	<b>microns</b>	NF EN ISO 534 NFQ 03 016
<b>Bulk</b>	<b>1,36</b>	<b>1,31</b>	<b>cm3/g</b>	NF EN ISO 534 NFQ 03 016
<b>Bendtsen smoothness</b>	<b>185</b>	<b>185</b>	<b>ml/min</b>	ISO 8791-2 NF Q 03-049
<b>Absolute humidity</b>	<b>4,50</b>	<b>5,00</b>	<b>%H2O</b>	NF EN ISO 20287 NFQ 03 003
<b>Relative humidity</b>	<b>30</b>	<b>38</b>	<b>% H2O in the air</b>	sword
<b>Permanence</b>	<b>ISO 9706</b>	<b>ISO 9706</b>		NF EN ISO 9706

