

Average characteristics				
GRADE	Trophée tints			
Forestry certification	FSC			
Fibre composition	ECF	ECF		
Medium	neutral	neutral		
Substance	80	160	g/m2	NF EN ISO 536 NFQ 03 019
Thickness	109	210	microns	NF EN ISO 534 NFQ 03 016
Bulk	1,36	1,31	cm3/g	NF EN ISO 534 NFQ 03 016
Bendtsen smoothness	185	185	ml/min	ISO 8791-2 NF Q 03-049
Absolute humidity	4,50	5,00	%H2O	NF EN ISO 20287 NFQ 03 003
Relative humidity	30	38	% H2O in the air	sword
Permanence	ISO 9706	ISO 9706		NF EN ISO 9706

