

<b>TECHNICAL DATA SHEET</b>			
<b>Paper name</b>	<b>Evercopy Colour Laser</b>		
<b>Fiber supply</b>	<b>100% recycled</b>		
<b>Ph</b>	<b>neutral</b>		
<b>Basis weight</b>	<b>100</b>	<b>g/m2</b>	NF EN ISO 536 NFQ 03 019
<b>Thickness</b>	<b>105</b>	<b>µm</b>	NF EN ISO 534 NFQ 03 016
<b>Bulk</b>	<b>1,05</b>	<b>cm3/g</b>	NF EN ISO 534 NFQ 03 016
<b>Whiteness</b>	<b>145</b>	<b>CIE</b>	NF ISO 11475 NFQ 03 099
	<b>100</b>	<b>ISO</b>	NFQ 03 039 ISO 2470
<b>Bekk Smoothness</b>	<b>120</b>	<b>s</b>	ISO 8791-2 NF Q 03-049
<b>Opacity</b>	<b>96</b>	<b>%</b>	NF ISO 2471 NFQ 03 040
<b>Absolute moisture content</b>	<b>4,50</b>	<b>%H2O</b>	NF EN ISO 20287 NFQ 03 003
<b>Relative humidity</b>	<b>30</b>	<b>in air</b>	
<b>Permanence</b>	<b>ISO 9706</b>		NF EN ISO 9706
<b>Environmental labels</b>	<b>FSC recycled, Blue Angel &amp; APUR</b>		

<b>TECHNICAL DATA SHEET</b>			
<b>Paper name</b>	<b>Evercopy Colour Laser</b>		
<b>Fiber supply</b>	<b>100% recycled</b>		
<b>Ph</b>	<b>neutral</b>		
<b>Basis weight</b>	<b>120</b>	<b>g/m2</b>	NF EN ISO 536 NFQ 03 019
<b>Thickness</b>	<b>126</b>	<b>µm</b>	NF EN ISO 534 NFQ 03 016

<b>Bulk</b>	<b>1,05</b>	<b>cm3/g</b>	<b>NF EN ISO 534 NFQ 03 016</b>
<b>Whiteness</b>	<b>145</b>	<b>CIE</b>	<b>NF ISO 11475 NFQ 03 099</b>
	<b>100</b>	<b>ISO</b>	<b>NFQ 03 039 ISO 2470</b>
<b>Bekk Smoothness</b>	<b>120</b>	<b>s</b>	<b>ISO 8791-2 NF Q 03-049</b>
<b>Opacity</b>	<b>98</b>	<b>%</b>	<b>NF ISO 2471 NFQ 03 040</b>
<b>Absolute moisture content</b>	<b>4,50</b>	<b>%H2O</b>	<b>NF EN ISO 20287 NFQ 03 003</b>
<b>Relative humidity</b>	<b>30</b>	<b>in air</b>	
<b>Permanence</b>	<b>ISO 9706</b>		<b>NF EN ISO 9706</b>
<b>Environmental labels</b>	<b>FSC recycled, Blue Angel &amp; APUR</b>		

<b>TECHNICAL DATA SHEET</b>			
<b>Paper name</b>	<b>Evercopy Colour Laser</b>		
<b>Fiber supply</b>	<b>100% recycled</b>		
<b>Ph</b>	<b>neutral</b>		
<b>Basis weight</b>	<b>160</b>	<b>g/m2</b>	<b>NF EN ISO 536 NFQ 03 019</b>
<b>Thickness</b>	<b>168</b>	<b>µm</b>	<b>NF EN ISO 534 NFQ 03 016</b>
<b>Bulk</b>	<b>1,05</b>	<b>cm3/g</b>	<b>NF EN ISO 534 NFQ 03 016</b>
<b>Whiteness</b>	<b>145</b>	<b>CIE</b>	<b>NF ISO 11475 NFQ 03 099</b>
	<b>100</b>	<b>ISO</b>	<b>NFQ 03 039 ISO 2470</b>
<b>Bekk Smoothness</b>	<b>120</b>	<b>s</b>	<b>ISO 8791-2 NF Q 03-049</b>
<b>Opacity</b>	<b>99</b>	<b>%</b>	<b>NF ISO 2471 NFQ 03 040</b>

<b>Absolute moisture content</b>	<b>4,50</b>	<b>%H2O</b>	<b>NF EN ISO 20287 NFQ 03 003</b>
<b>Relative humidity</b>	<b>30</b>	<b>in air</b>	
<b>Permanence</b>	<b>ISO 9706</b>		<b>NF EN ISO 9706</b>
<b>Environmental labels</b>	<b>FSC recycled, Blue Angel &amp; APUR</b>		