



Technical Data: LYRECO PREMIUM

			80
Basis weight	g/m ²	ISO 536	80 ± 3.0
Caliper	µm	ISO 534	107 ± 3
Roughness Bendtsen	ml/min	ISO 8791-2	150 ± 50
Opacity	%	ISO 2471	94.0
Moisture abs.	%	ISO 287	5.0 ± .5
Brightness UV	%	ISO 2470	114.0 ± 2.0
CIE Whiteness	%	ISO 11475	170 ± 4.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper.
 Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA