










555A-M

LLDPE cast stretch film, made of **60% Post-Consumer Recycled** raw materials and 40% virgin raw materials. 555 is suitable for **wrapping machines without prestretch group and for hand wrap**. Thickness downgauging maintaining the same performance allows 555 to replace any kind of standard film saving up to 50% material.

Characteristic	Method	Unit	Direction	9 μm	12 μm	15 μm	Tolerances
Impact resistance	ASTM D1709 A	g	-	28	40	59	10%
Tensile strength at break	ASTM D882 B	MPa	Machine Direction	33	23	29	10%
			Transversal Direction	19	17	17	10%
Tensile strength at yield	ASTM D882 B	MPa	Machine Direction	26	15	16	10%
			Transversal Direction	6	4.2	6	10%
Elongation at break	ASTM D882 B	%	Machine Direction	190	201	300	10%
			Transversal Direction	490	540	560	10%
Tear Resistance	ASTM D1922	mN	Machine Direction	230	250	350	10%
			Transversal Direction	2224	2740	3692	10%
Stretch	Hipac	%	-	50	70	90	5%
Cling	Hipac	g	-	135	135	125	10%

In case of additives these values should be reduced by 5%.





This film has been manufactured with 60% of Post-Consumer Recycled plastic. It may contain small imperfections and gels, as a proof of its actual inclusion.

Small variations in colour and mechanical properties could occur from batch to batch.

Your cooperation will help us reducing the environmental impact of our products.

Coloured	Slippery	AUV 6/12 months	Antistatic	Cling Out/In/Both	Low Temperature	Printed	Double Edges
×	V		₹	V	√	×	\checkmark

The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. Products in conformity with our Technical Specification. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.

Visit us at www.hipac.eu Release 2022-1