

TECHNICAL DATA SHEET

Office Standard Cut-Size

Physical Parameters

	REFERENCE	TARGET	TYPICAL VALUES	
Basis Weight, g/m ²	ISO 536	70.0	67.2	72.8
Thickness, μm	ISO 534	101	96.0	106
Stiffness MD, mN	ISO 2493-1		≥ 90	
Stiffness CD, mN	ISO 2493-1		≥ 30	
Tensile MD, kN/m	ISO 1924-2		≥ 4.5	
Bendtsen Roughness, ml/min	ISO 8791-2	230	160	300
Air Permeability, ml/min	ISO 5636-3		≤ 1700	
Moisture, %	ISO 287	4.0	3.5	4.5
Formation, #	Internal Method		≥ 25	

Optical Parameters

	REFERENCE	TARGET	TYPICAL VALUES	
Whiteness, CIE	ISO 11475	161	158	164
Brightness D65, %	ISO 2470-2	110	107	113
Opacity, %	ISO 2471	91	≥ 89	

Approved by:

Technical Department: Eng. Cidália Torre Abreu



MANAGEMENT SYSTEMS INFORMATION

- The Navigator Company's papers are made from Elemental Chlorine Free (ECF) bleached kraft pulp;

- The Navigator Company's papers are produced in a neutral/slightly alkaline papermaking process, therefore considered as "acid free" products which meet the requirements of ISO 9706 standard, "*Information and documentation – Paper for documents – Requirements for permanence*";

- The Navigator Company's laboratories are accredited according to the ISO 17025 standard;

- Quality, Environmental, Health, Safety and Energy Management Systems are certified according to the ISO 9001, ISO 14001, ISO 45001 and ISO 50001 standards;

- The Navigator Company is chain-of-custody certified according to standards FSC-STD-40-004 and FSC-STD-40-005 (NC-COC/CW-014433) and to standard PEFC ST 2002 (APCER-PEFC-COC-070008).