



**DCP is the ideal medium for any document containing more color illustrations than text.** Its high whiteness and perfectly smooth surface promote high quality color reproduction.

Substance	gsm	NF EN ISO 536	(+/-2,5%)	80	90	100	120	160	200	250	300	350	400
<b>Thickness</b>	µm	NF EN ISO 534	(+/-5)	92	99	110	128	160	200	230	276	322	370
<b>Bulk</b>	cm <sup>3</sup> /g	NF EN ISO 534		1.15	1.10	1.10	1.07	1.00	1.00	0.92	0.92	0.92	0.92
<b>Whiteness</b>	CIE	NF ISO 11475	(+/-3,5%)	170	170	170	170	170	170	170	170	170	170
	ISO	ISO 2470-2		111	111	111	111	111	111	111	111	111	111
<b>Absolute humidity</b>	%H <sub>2</sub> O	NF EN ISO 20287		4,5	4,5	4,5	4,5	4,8	4,8	5,2	5,7	5,7	5,7
<b>Relative humidity</b>	% in the air	Sword measurement		32	32	32	32	35	35	40	46	46	46
<b>Opacity</b>	%	NF ISO 2471	(+/-3)	93,5	95	96	97	>99	>99	>99	>99	>99	>99
<b>Bekk smoothness</b>	s	NF ISO 5627		150	150	150	150	150	150	140	125	110	110

## Application

External communication. All documents containing text and colors. Reproduction of images.

## Product certificates and technical information

- Resistant to ageing (ISO 9706)
- ColorLok technology



## Product certificates and environmental information

- FSC®
- Ecolabel



## Information for printing

- Certified for professional dry toner systems (DIN / EN 12281)
- Recommended for all black and colour office printing technologies: laser with dry toner, solvent-free inkjet, solid wax ink
- Plain paper setting for inkjet printing

## Mill certifications

- ISO 14001: Environmental management system
- ISO 9001: Quality management system
- ISO 50001: Energy management system

Made in France

Indicative values. Errors and omissions excepted. Subject to change without notice.  
Revision date: 2023/02/17