

Average specifications			
Grade	2547 / 2651		
Forestry Certification			
Pulp	ECF		
Medium	neutral		
Substance	80	gsm	NF EN ISO 536 NFQ 03 019
Thickness	110	microns	NF EN ISO 534 NFQ 03 016
Bulk	1,38	cm3/g	NF EN ISO 534 NFQ 03 016
Whiteness	170	Cie	NF ISO 11475 NFQ 03 099
	116	ISO	NFQ 03 039 ISO 2470
Bendtsen smoothness	160	ml/min	ISO 8791-2 NF Q 03-049
Absolute humidity	5,00	%H2O	NF EN ISO 20287 NFQ 03 003
Relative humidity	38	in the air	sword
Opacity	93	%	NF ISO 2471 NFQ 03 040
Kajaani formation	89		
Permanence	ISO 9706		NF EN ISO 9706