

ACONDICIONAMIENTO TARRASENSE
LEITAT

NUM. 700.666/1-E
HOJA 7 / 7

CHARACTERISTICS	STANDARD	SPECIFIED VALUE	OBTAINED VALUE	QUALIFICATION
4.3.2. MECHANICAL HAZARDS				
ABRASIÓN RESISTANCE Original	EN 388 6.1	≥ 500 (Level 2)	1000	COMPLIES LEVEL 2
BLADE CUT RESISTANCE Index (I) Original	EN 388 6.2	> 2,5 (Level 2)	3,18	COMPLIES LEVEL 2
TEAR RESISTANCE Original	EN 388 6.3	≥ 75 N (Level 4)	78,0 N	COMPLIES LEVEL 4
PUNCTURE RESISTANCE Original	EN 388 6.4	≥ 60 N (Level 2)	60,5 N (Level 2)	COMPLIES LEVEL 2

Terrassa, 27th November 2007

HEAD TECHNICIAN
Marta Torras Arco
Industrial T. Engineer


