

Physical Properties	Test Method	Unit	Value
Corrugated cardboard	-	-	E-flute 1,40 brown/brown
Dimension width length	-	mm	870 460
Edge crush resistance	DIN EN ISO 3037	kN/m	5.5
Penetration test	DIN 53142-1	J	4.0
Bursting strength	DIN EN ISO 2759	kPa	1200
Printing ink	-	-	Water based
Closure	-	-	Flap
Film type	-	-	60 MX- Polyolefin film
Thickness	-	mμ	60
Thickness tolerance	-	%	+ - 15
Position tolerance	-	mm	+ - 10
Adhesive	-	-	Water based
Glue pad	-	mm	12
Glue pad tolerance	-	mm	+ - 3
<b>Testing Standard</b>	The packaging materials were tested according to DIN ISO 187 at 23°C and 50% relative humidity.		

NOTICE: While values shown are typical of this product, they should not be construed as specific limits. Sealed Air makes no warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, with respect to any product, information or recommendations referred to herein, and shall not be liable for any loss or damage, directly or indirectly, related to such product, information or recommendations or for consequential or incidental damages. User should test each application to determine suitability of the product for the intended use.